



Repair Putty All-Purpose

Description: Loctite Repair Putty All-Purpose is a hand-mixable and fast-setting two-part adhesive consisting of an epoxy resin putty and a hardener putty perfect for small or emergency repairs. The two parts react to produce a hard, tough, permanent and waterproof bond on a wide range of materials. The modeling clay consistency allows it to be shaped and formed as desired before curing begins. Loctite Repair Putty All-Purpose does not shrink and is resistant to most common solvents. It can bond to damp surfaces, cure under water and can be sanded, drilled and painted after 60 minutes. Loctite Repair Putty All-Purpose will rebuild and bind to create a waterproof seal that is potable water safe as certified by NSF®.

Available As:

Item #	Size	Package
1999131	2 oz (56 g)	Carded Cylinder

Features & Benefits:

- Easy to Use – Knead, Apply, Ready
- Waterproof
- Paintable & Sandable
- Quick Drying Time
- Certified to NSF/ANSI 61

Recommended For:

Loctite Repair Putty All-Purpose is suitable for use on plumbing, tubs & showers, pipes, potable water tanks, fiberglass, marine & pool, ceramic, PVC, aluminum, wood, brick, metal, concrete, rigid and semi-flexible plastic. It bonds metal, wood, ceramic, brick, most plastics* and concrete.

It will rebuild and bind to create a waterproof seal that is potable water safe. It will fill in gaps or reconstruct part, making it ideal for 3-D repairs and projects.

For Best Results:

- *Not recommended for polyethylene, polypropylene, non-stick coatings, nylon products or flexible materials
- Not suitable for applications above 250°F (121°C) for fills or applications greater than 158°F (70°C) for load bearing bonds
- Do not use for structural applications
- Not for use for large and deep holes
- Not suitable for repairs subject to movement



TECHNICAL DATA SHEET

Typical Uncured Physical Properties:

Color:	Blue and White
Appearance:	Putty
Base:	Epoxy resin / Polysulfide hardener
Odor:	Mild amine
Density:	
Hardener:	2 g/ml
Resin:	2 g/ml
Shelf Life:	24 months from date of manufacture (unopened)
Lot Code Explanation:	YYDDD
Stamped on foil seal of tube	YY = Last two digits of year of manufacture DDD = Day of manufacture based on 365 days in a year Example: 14061 = 61st day of 2014 = March 2, 2014

Typical Application Properties:

Application Temperature:	Apply between 39°F (4°C) to 95°F (35°C). For best results, apply at room temperature.
Working Time:	3-5 minutes*
Handling Time (can be sanded, drilled, painted):	15 minutes*
Functional Cure Time:	60 minutes*
Full Cure Time:	24 hours*
	*Time is dependent on temperature, humidity and thickness of putty applied

Typical Cured Performance Properties:

Color:	Bluish white	
Cured Form:	Hard solid	
Service Temperature:	-17°F (-27°C) to 250°F (121°C) -17°F (-27°C) to 158°F (70°C)	For Fills For Load-bearing Bonds
Water Resistant:	Yes	
Sandable:	Yes	
Paintable:	Yes	
Hardness:	84	Shore D
Shear Strength:		
Steel, 24h cure:	1703 ± 58 psi (11.7 ± 0.4 N/mm ²)	
Steel, 24h cure, wet substrate:	747 ± 91 psi (5.2 ± 0.6 N/mm ²)	
Beech, 24h cure:	969 ± 26 psi (6.7 ± 0.2 N/mm ²)	
Beech 24h cure, wet substrate:	207 ± 44 psi (1.4 ± 0.3 N/mm ²)	
Shear Strength - Underwater Bonding, 24 h cure:		
Steel, tested wet:	593 ± 260 psi (4.1 ± 1.8 N/mm ²)	
Steel, tested 24h dry cure:	451 ± 352 psi (3.1 ± 2.4 N/mm ²)	
Specifications:	Certified to ANSI/NSF Standard 61 for drinking water contact	



TECHNICAL DATA SHEET

Directions:**Tools Typically Required:**

Knife, sandpaper or wire brush, damp cloth

Safety Precautions:

Wear gloves and wash hands after use.

Preparation:

Surfaces should be clean, dry and free from grease, dust and oil. For better adhesion, slightly roughen the surface with a wire brush or sandpaper prior to cleaning. Cut off desired amount of Repair Putty and knead until uniform color is obtained (approximately 1 minute).

Application:

Apply the putty to surface to be repaired within 3 minutes of mixing. Work putty firmly into the crack or hole and shape/smooth with hands. For bonding, place the putty between the surfaces and apply firm pressure to ensure intimate contact with both surfaces. If applying to a wet surface, apply forcefully and hold in place for 3-5 minutes until adhesion takes effect. For a smooth finish, rub the putty with a damp cloth prior to hardening. Working time is approximately 3-5 minutes. After 15-60 minutes, the putty can be sanded, drilled or painted. For best results: Use damp fingers for easier mixing, application and to achieve a smooth appearance of the cured putty. Remove excess material before hardening begins.

Clean-up:

Cured and uncured putty may be cut away with caution using a sharp blade.

Storage & Disposal:

Not damaged by freezing. Store unused product in a tightly sealed container. Knead unwanted putty, allow to harden and dispose with trash. Product should be stored at room temperature.

Label Precautions:

WARNING: MAY CAUSE ALLERGIC SKIN REACTION. EYE, SKIN AND RESPIRATORY IRRITANT.

WARNING: Contains epoxy resins, amine curing agents and talc. Avoid contact with eyes and prolonged contact with skin. Wear impervious gloves. Wash hands after using. Do not breathe fumes/dust while sanding. **FIRST AID:** For eye contact, flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water. Call a physician if irritation develops or persists. If swallowed, do not induce vomiting; call a physician or Poison Control Center.

WARNING: This product contains a chemical known to the State of California to cause cancer. **KEEP OUT OF THE REACH OF CHILDREN.**

Refer to the Safety Data Sheet (SDS) for further information.

Disclaimer:

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Trusted Performance. Proven Results.

For over 50 years, Loctite Brand adhesives and sealants have taken on the toughest jobs. Used in race cars, airplanes, and even in the space-shuttle, Loctite provides solutions for the most demanding industrial, professional and consumer applications. Loctite gives you not the specialization, power and performance to not only get your job done, but to get it done right.

1-800-624-7767 – Mon-Fri - 9:00a – 4:00p ET

www.loctiteproducts.com

Loctite Brand is part of the Henkel family of brands. Founded in 1876, Henkel is a global leader in the consumer and industrial businesses. Henkel operates worldwide with leading brands and technologies in three business areas: Laundry & Home Care, Beauty Care and Adhesive Technologies.

Henkel Corporation - Professional & Consumer Adhesives Headquarters - Rocky Hill, CT 06067

www.henkelna.com

Revision Date: 04/08/2016 Supercedes: NEW Ref. #: FCB

